

Sonolytic Oxidation of Tc(IV)O₂nH₂O Nanoparticles to Tc(VII)O₄ in Aqueous Solution

by Muhammad Zakir

FILE	26_7-19-1-PB_1_1.PDF (209.87K)	WORD COUNT	3523
TIME SUBMITTED	19-OCT-2020 04:46PM (UTC+0700)	CHARACTER COUNT	17624
SUBMISSION ID	1419662157		

Sonolytic Oxidation of Tc(IV)O₂·nH₂O Nanoparticles to Tc(VII)O₄ in Aqueous Solution

M. Zakir^{1*}, T. Sekine²

¹ Department of Chemistry, Hasanuddin University, Indonesia

² Graduate School of Science, Tohoku University, Sendai, Japan

ARTICLE INFO

Article history:

Received 20 November 2009

Received in revised form 14 April 2010

Accepted 18 April 2010

Keywords:

Tc-nanoparticles

Sonolytic oxidation

Tc(IV), Tc(VII)

ABSTRACT

Sonolysis of a hydrosol of TcO₂·nH₂O was investigated in the Ar- or He-atmosphere. Colloidal TcO₂·nH₂O nanoparticles were irradiated with a 200 kHz and 1.25 W/cm² ultrasound. It was found that the TcO₂·nH₂O colloids dispersed in an aqueous solution (under Ar or He atmosphere) was completely dissolved by ultrasonic irradiation (200 kHz, 200 W). The original brownish black color of the suspension suddenly disappeared leaving behind a colorless solution. This change suggests that oxidation of Tc(IV) to Tc(VII) takes place. The oxidation was almost complete during 30 minutes sonication time under argon atmosphere for initial concentration of 6.0E-5 M. Addition of *t*-butyl alcohol, an effective radical scavenger which readily reacts with OH radicals, suppressed the dissolution of TcO₂·nH₂O colloids. This reaction indicates that TcO₂·nH₂O molecules are oxidized by OH radicals produced in cavitation bubbles

© 2010 Atom Indonesia. All rights reserved

INTRODUCTION

The chemical effects of ultrasound derive primarily from acoustic cavitation, namely the formation, growth, and implosive collapse of tiny bubbles in the medium. Bubble collapse in liquids results in an enormous concentration of energy from the conversion of the kinetic energy of the liquid motion into heating of the contents of the bubble. The high local temperatures and pressures, combined with extraordinarily rapid cooling, provide a unique means for driving chemical reactions under extreme conditions [1].

The interactions of ultrasound in aqueous solution are often similar to those of ionizing radiation. For example, H₂ and H₂O₂ are formed [2], while H atoms and OH radicals can be traced by spin trapping [3]. However, dissolved substances often experience chemical changes which cannot be understood simply in terms of attack by H or OH radicals. A typical example is the production of hydrogen in aqueous solution of 2-propanol (< 0.1 M), where it was shown by isotopic labeling that the hydrogen originated mainly from the alcohol [4]. The effect was explained by a thermal dehydrogenation of 2-propanol as the alcohol evaporates into the cavitation bubbles, in which the chemical effects are initiated by the high temperatures produced in the adiabatic compression

phase or collapse of the bubbles. These temperatures may amount to several thousands kelvin [5].

A number of metal nanoparticles have been prepared by means of ultrasonic irradiation. Some examples that can be cited here are colloidal gold nanoparticles [6,7], Au/Pd bimetal nanoparticles [8], Pt nanoparticles [9], Pd nanoparticles [10], and Ag nanoparticles [11]. It is believed that OH radical and H atoms are responsible in the preparation of those metal nanoparticles. Some metals, however, demonstrate special properties in which they can only be reduced sonolytically by appropriate reducing agents, for example Rh(III) was successfully reduced by transforming OH radicals into highly reducing radicals [12]. This phenomena might be valid to Tc where this metal could only be reduced by a specific reducing agent. Our initial experiment showed that Tc could not be reduced by the recommended reducing agents available currently in the literature [13].

In addition, a recent review describes that there is a considerable interest in the sonochemistry of aqueous solution from the point of view of environmental remediation [14], for instance to eliminate undesirable chemical compounds in hazardous waste treatment. Ultrasonic irradiation has been utilized in the past years as a novel advanced oxidation process to answer the growing need for lower levels of contaminants in wastewater

*Corresponding author.

E-mail address: muhammadzakir@gmail.com (M. Zakir)

[15]. Thus, the sonochemical method is expected to be promising in the handling of high level nuclear waste in the future, especially technetium [16]. However, there is a very limited literature concerning the redox properties of technetium under ultrasonic irradiation.

Understanding the sonolytically induced redox properties of technetium is very important in order to prepare Tc nanoparticles for pharmaceutical use and catalyst [17], and to properly handle this radionuclide in the environment. In addition, sonolytic effects can be easily controlled in the use of this method for specific purposes, for instance redox or dissolution reactions of radionuclides in the nuclear waste.

This paper describes the oxidation processes of $Tc(IV)O_2 \cdot nH_2O$ nanoparticles to aqueous solution of $Tc(VII)O_4^-$. The oxidation mechanism from $Tc(IV)$ to $Tc(VII)$ is discussed. It is expected that understanding on the sonolytic oxidation of $Tc(IV)$ will facilitate the study of redox properties of technetium under sonication in the future.

EXPERIMENTAL METHODS

Irradiation system

Ultrasonic irradiation was carried out using an oscillator of 65 mm in diameter (Kaijo; MFG. No. 5N11) and an ultrasonic generator (Kaijo 4021type; frequency 200 kHz), which was operated at 200 W. The reaction vessel was mounted at a constant position. The bottom of the vessel was 4.0 mm distant from the top of the oscillator. A 10 ml of Ar- or He-saturated hydrosol containing $TcO_2 \cdot nH_2O$ nanoparticles was sonicated in the water bath which was maintained at 20°C by a water circulation system (SCINICS CH-201). The reaction vessel was closed from the air during the irradiation in the Ar- or He- atmosphere. The sonication time was 5 – 90 min. A schematic illustration of the ultrasonic irradiation system was shown in Fig. 1. The temperature of targets was monitored with a thermometer dipped in the water bath.

Sample Preparation

Technetium(IV) oxide colloid hydrosol was prepared from bremsstrahlung irradiation of aqueous pertechnetate (TcO_4^-) solution. The colloid was separated from unreduced pertechnetate by ultrafiltration. Concentration of the hydrosol of $TcO_2 \cdot nH_2O$ colloid stock is $1.24E-3$ M. The sample for ultrasonic irradiation was prepared from the stock hydrosol by dilution with triply distilled water.

Final concentration of the hydrosols were adjusted to the range of $1.0E-5$ to $1.2E-4$ M. The sample was poured into the sonication vials (10 ml in volume) and was bubbled with Ar, or He, respectively.




Fig. 1. Schematic view of the ultrasonic irradiation system.

A = water circulation and temperature control system (SCINICS CH-201); B = cooling water bath; C = ultrasonic generator (Kaijo 4021type; Lot. No. 54H6, Frequency: 200 kHz); D = silicon rubber septum; E = ultrasonic transducer (diameter: 65 mm; Kaijo; MFG. No. 89J5); F = quartz cell for UV-Vis measurement; G = glass reaction vessel; H = thermometer.

Determination of formation rate of OH radicals

The formation rate of H_2O_2 and OH radical during the sonolysis of the Ar-saturated, or He-saturated water were estimated by a method similar to Fricke dosimetry[18]: a 10 ml of Ar-saturated (d/or He) aqueous solution containing 50 mM $Fe(NH_4)_2(SO_4)_2$ and 0.8 N H_2SO_4 was irradiated and then the amount of Fe(III) ions ($\epsilon = 2194 M^{-1}cm^{-1}$, $\lambda = 304$ nm) formed from the H_2O_2 and OH radical oxidation of Fe(II) was spectrophotometrically determined.

Technetium Analyses

The UV-visible spectra of $Tc(VII)$ were recorded on a Shimadzu MultiSpec-1500 in the range from 190 to 800 nm. The concentration of pertechnetate was determined by the optical absorption ($\epsilon = 622 M^{-1} cm^{-1}$ at $\lambda = 244$ nm, and $\epsilon = 236 M^{-1} cm^{-1}$ at $\lambda = 287$ nm, where ϵ represents the molar absorption coefficient at the corresponding wavelength λ [19,20]. The fraction of $^{99}TcO_2 \cdot nH_2O$ colloid in sample is determined by imaging analysis of thin layer chromatography (TLC) plate. TLC was performed using Merk

60 F₂₅₄ precoated silica gel plate (0.2 mm in thickness). Radioactivity of technetium-99 species on TLC-plate visualized with using an imaging plate (Fuji Photo Film, BAS-IP SR 2025) were analyzed by a Bio Imaging Analyzer (Fuji Photo Film, BAS-5000).

RESULTS AND DISCUSSION

Estimation of the production rate of OH radicals

The absorption spectra of formation of Fe(III) were recorded during the sonolysis of Ar- or He-saturated of Fe(II) aqueous solutions. The amount of Fe(III) formed was calculated by using the ϵ value = $2194 \text{ M}^{-1} \text{ cm}^{-1}$ at $\lambda = 304 \text{ nm}$. The results were shown in Table 1.

Table 1. Results from the calculation of Fe³⁺ concentration in the sonolysis of Fe²⁺ aqueous solution under (a) Ar and (b) He atmosphere, respectively. The average of formation rates were $28.1 \pm 2.70 \mu\text{M} \cdot \text{min}^{-1}$ under Ar, and $11.6 \pm 1.20 \mu\text{M} \cdot \text{min}^{-1}$ under He, respectively.


(a) Argon atmosphere

Sonication time/min	[Fe ³⁺] (M)	Rate (M. min ⁻¹)
0	0	0
5	1.60E-4	3.20E-5
10	2.96E-4	2.96E-5
15	4.34E-4	2.89E-5
20	5.56E-4	2.78E-5
25	6.59E-4	2.64E-5
30	7.23E-4	2.41E-5
Average		$2.81 \pm 0.27 \text{E-5 M} \cdot \text{min}^{-1}$

(b) Helium atmosphere

Sonication time/min	[Fe ³⁺] (M)	Rate (M. min ⁻¹)
0	0	0
5	4.79E-5	9.58E-6
10	1.08E-4	1.08E-5
15	1.78E-4	1.18E-5
20	2.50E-4	1.25E-5
25	3.08E-4	1.23E-5
30	3.78E-4	1.26E-5
Average		$1.16 \pm 0.12 \text{E-5 M} \cdot \text{min}^{-1}$

The oxidation of Fe²⁺ by OH radicals can be simply written down as



Hence, the amount of OH radicals formed in the sonolysis of water can be estimated from the amount of Fe³⁺ in the solutions. The rate of Fe(III) formation

were found to be $28.1 \pm 2.70 \mu\text{M} \cdot \text{min}^{-1}$ under argon, and $11.6 \pm 1.20 \mu\text{M} \cdot \text{min}^{-1}$ under helium, respectively. Therefore, the OH formation rates of each gas condition in this experiment were estimated to be $28.1 \pm 2.70 \mu\text{M} \cdot \text{min}^{-1}$ under argon, and $11.6 \pm 1.20 \mu\text{M} \cdot \text{min}^{-1}$ under helium.

The OH-radical production depends on the nature of the operating gas. The temperature reached in the compressed bubble depends mainly on the ratio of specific heats C_p/C_v of the gas and its thermal conductivity. The presence of water vapour and of other polyatomic volatile components of the solution will depress the value of C_p/C_v below that of a pure monoatomic or diatomic gas. Any endothermic reaction will further depress this ratio as it acts to increase the apparent heat capacity. In the perfectly adiabatic limit, T_{max} and V_{min} of the collapsed bubble are linked by the expression $T_{\text{max}}/T_0 = (V_0/V_{\text{min}})^{C_p/C_v-1}$, wherefrom it is seen that in a situation where C_p/C_v approaches unity, the temperature rise must be small even at high compression ratios [21]. Further, the higher the thermal conductivity, the more efficient the heat transfer out of the compressed bubble. The ratio C_p/C_v between He and Ar is almost the same (Table 2), but thermal conductivity of He is much higher than Ar, so that under He, the OH-radical yield is about three times lower than under argon atmosphere. The trend of increasing OH-radical yield with decreasing heat conductivity in the noble gases is well established [22, 23].

Table 2. Effect of saturating gases properties on OH formation rate in pure water

Saturating gas	OH formation rate ^a $\mu\text{M} \cdot \text{min}^{-1}$	Thermal conductivity (σ), milliwatt $\text{m}^{-1}\text{K}^{-1}$ (300K)	Polytropic index, $\gamma = C_p/C_v$ (25°C)
Helium	11.6 ± 1.20	156.7	1.67
Argon	28.1 ± 2.70	17.9	1.68

^aAverage value obtained from Table 1

This can be attributed to a difference of the effective maximum temperature in the collapsing bubbles. Because the thermal conductivity of He is larger than that of Ar, thermal transport effectively occurs from the bubbles to the surrounding liquid. Thus, cavitation bubbles filled with He should be cooler than those filled with Ar, resulting in the slower OH formation rate.

Sonolysis of aqueous solution of TcO₂·nH₂O nanoparticles

Sonolysis of TcO₂·nH₂O colloids dispersed in aqueous solution was investigated under Ar or He atmosphere. Gradual oxidation was observed from

the $Tc(IV)O_2 \cdot nH_2O$ colloid to TcO_4^- . The original brownish black color of the suspension disappeared leaving behind a colorless solution. The oxidation was completed during 30 minutes sonication time under argon atmosphere for initial concentration of $6.0 \times 10^{-5} M$ as can be seen in the UV-Vis spectra (Fig. 2). Helium atmospheres did not show the same courses. It took 60 minutes to have the oxidation went to completion. The characteristics absorption peaks of pertechnetate were clearly appeared at the 30 min sonication. Fig. 2 shows the changes in the absorption spectra during sonication, both under Ar and He.




Fig. 2. Changes in the absorption spectra during sonication of $TcO_2 \cdot nH_2O$ colloids dispersed in aqueous solution. (a) Ar and (b) He. Cell length: 1 cm.

The amounts of $Tc(IV)O_2 \cdot nH_2O$ and $Tc(VII)O_4^-$ in the samples were determined by thin layer chromatography (TLC). Imaging analysis of the TLC-plates of the samples clearly shows the disappearance of $TcO_2 \cdot nH_2O$ colloid spot on the plate after ultrasonic irradiation. The retardation factor (R_f) for $Tc(IV)$ is 0 and $Tc(VII)$ is 0.7, respectively. Both sample's image and its Photostimulated Luminescence (PSL) spectra were recorded during the imaging analysis. The total activity before sonication was 17399 dpm, while after sonication was 17250 dpm. This suggests that $Tc(IV)O_2 \cdot nH_2O$ colloids were oxidized to $Tc(VII)O_4^-$.

Since $TcO_2 \cdot nH_2O$ used in the present study is a non-volatile compound, the solute does not pyrolyze in the cavitation bubbles. To confirm the reaction pathway, the effect of the radical scavenger, *t*-butyl alcohol ($(CH_3)_3COH$), on the rate of $TcO_2 \cdot nH_2O$ dissolution was investigated in an Ar

atmosphere (Fig. 3). *t*-Butyl alcohol readily reacts with OH and H radicals [24, 25]. The production of TcO_4^- was considerably suppressed in the presence of *t*-butyl alcohol (an effective scavenger of OH radicals), indicating that Tc was oxidized by OH radicals produced in cavitation bubbles.





Fig. 3. Effects of radical scavenger addition (*t*-butyl alcohol) on the rate of decomposition of $TcO_2 \cdot nH_2O$. Ar-atmosphere, $[TcO_2 \cdot nH_2O]_0 = 6 \times 10^{-5} M$.


The oxidation reaction of Tc must compete with the recombination reaction of OH radicals in the bulk solution region as follows:



It should be recalled that H_2O_2 produced from the recombination of OH radicals is a nice oxidizing agent for $TcO_2 \cdot nH_2O$.

Mechanisms of sonolytic oxidation of $TcO_2 \cdot nH_2O$ nanoparticles

The mechanisms involved in the dissolution of colloidal $TcO_2 \cdot nH_2O$ nanoparticles should be considered with regard to the species generated from the water molecules by absorption of ultrasound. The species, as mentioned above, are originated from the following reactions.



It has been proposed that during the sonochemical treatments of many organic compounds in water [23,26], the oxidative decomposition generally proceeds via the reaction with OH radicals which are formed from water pyrolysis in the collapsing hot bubbles (3). Particularly in the case of volatile or hydrophobic compounds, the decomposition proceeds not only via OH radicals reaction but also via a direct pyrolysis reaction in the collapsing hot bubbles and the hot interface region [23,26].



² Cavitation near extended liquid-solid interfaces is very different from cavitation in pure liquids. Near a solid surface, bubble collapse becomes nonspherical, driving high-speed jets of liquid into the surface and creating shockwave damage to the surface. Because most of the available energy is transferred to the accelerating jet, rather than the bubble wall itself, this jet can reach velocities of hundreds of meters per second. In addition, shockwaves created by cavity collapse in the liquid may also induce surface damage and the fragmentation of brittle materials.

The impingement of microjets and shockwaves on the surface creates the localized erosion responsible for ultrasonic cleaning and many of the sonochemical effects on heterogeneous reactions. The importance of this process to corrosion and erosion phenomena of metals and machinery has been thoroughly reviewed elsewhere [27].

¹⁰ Those effects mentioned above may cause the destruction of the passivating film on the surface of $TcO_2 \cdot nH_2O$ nanoparticles and, accordingly, increase the rate of metal dissolution. Consequently, it seems that the dissolution of colloidal $TcO_2 \cdot nH_2O$ nanoparticles might take place in two steps. The first step is the state change of $TcO_2 \cdot nH_2O$ from the solid state into the ³⁹ solution state. The next step is a direct oxidation of $Tc(IV)$ species to $Tc(VII)$ species. Species generated from the water pyrolysis in the hot cavitation bubbles (or their recombination products) might be involved in the oxidation processes (3-6).

In summary, the dissolution mechanism of colloidal $TcO_2 \cdot nH_2O$ nanoparticles by ultrasonic irradiation could be proposed as follows.

First step: destruction of $TcO_2 \cdot nH_2O$ by shock waves generated from cavity collapses.




Second step: oxidation of $Tc(IV)$ species by either OH radicals or their recombination products.

(1) Water pyrolysis in the hot cavitation bubble (Reaction 3)


(2) ¹⁸ combination of radicals (Reaction 6)

(3) Oxidation of $Tc(IV)$ to $Tc(VII)$ by OH radicals


Triggering reaction:



Disproportionation reactions:



(4) Oxidation of $Tc(IV)$ by H_2O_2




CONCLUSIONS

$TcO_2 \cdot nH_2O$ colloids dispersed in an aqueous solution, under Ar or He atmosphere, was completely dissolved by ultrasonic irradiation (200 kHz, 200 W), and TcO_4^- was eventually produced. The ¹⁹ production of TcO_4^- was considerably suppressed in the presence of *t*-butyl alcohol (an effective ²⁸ scavenger of OH radicals), indicating that Tc was oxidized by OH radicals produced in cavitation bubbles. The formation rate of TcO_4^- under He atmosphere was slower than that under Ar atmosphere.

REFERENCES

1. K.S. Suslick, Science **247** (1990) 1439.
2. X. Fang, G. Mark, C. Von Sonntag, Ultrason. Sonochem **3** (1996) 57.
3. K. Makino, M.M. Mossoba, P. Riesz, J. Phys. Chem. **87** (1983) 1369.
4. M. Anbar, I.J. Pecht, J. Phys. Chem. **68** (1964) 1462.
5. B.E. Noltingk, E.A. Neppiras, Proc. Phys. Soc. London B **36** (1950) 674.
6. K. Okitsu, A. Yue, S. Tanabe, H. Matsumoto, Y. Yobiko, Langmuir **17** (2001) 7717.
7. J.E. Park, M. Atobe, T. Fuchigami, Ultrason. Sonochem **13** (2006) 674.
8. Y. Mizukoshi, T. Fujimoto, Y. Nagata, R. Oshima, Y. Maeda, J. Phys. Chem. B **104** (2000) 6028.
9. T. Nakagawa, H. Nitani, S. Tanabe, K. Okitsu, S. Seino, Y. Mizukoshi, T.A. Yamamoto, Ultrason. Sonochem **12** (2005) 249.
10. Y. Mizukoshi, R. Oshima, Y. Maeda, Y. Nagata, Langmuir **15** (1999) 2733.
11. Y. Mizukoshi, E. Takagi, H. Okuno, R. Oshima, Y. Maeda, Y. Nagata, Ultrason. Sonochem. **8** (2001) 1.
12. K. Okitsu, Y. Mizukoshi, H. Bandow, Y. Maeda, Y. Yamamoto, Y. Nagata, Ultrason. Sonochem. **3** (1996) 1.
13. M. Zakir, Ph.D. Thesis, Tohoku University, Sendai, Japan (2006).

14. R. Kidak, N.H. Ince, *Ultrason. Sonochem.* **13** (2006) 195.
15. Z. Guo, et al., *Ultrason. Sonochem.* **13** (2006) 471.
16. J.E.S. Cziganny, M. Flury, J.S. Harsh, *Environ. Sci. Technol.* **39** (2005) 1506.
17. K. Schwochau, *Technetium: Chemistry and Radiopharmaceutical Applications*, Wiley-Vch, Weinheim, Germany (2000).
18. Y. Nagata, Y. Mizukoshi, K. Okitsu, Y. Maeda, *Radiat. Res.* **146** (1996) 333.
19. L. Heller-Grossman, S. Abrashkin, A. Shafferman, M.A. Davis, R.A. Taube, *Int. J. Appl. Radiat. Isotopes* **32** (1981) 501.
20. K.B. Said, Y. Seimbille, M. Fattahi, C. Houee-Lévin, J.C. Abbé, *Appl. Radiat. Isot.* **54** (2001) 45.
21. W.B. McNamara III, Y.T. Didenko, K.S. Suslick, *Nature* **401** (1999) 772.
22. A. Henglein, *Naturwiss* **43** (1956) 277.
23. I. Hua, R.H. Hochemer, M. Hoffmann, *J. Phys. Chem.* **99** (1995) 2335.
24. M. Anbar, P. Neta, *Int. J. Appl. Radiat. Isotop.* **18** (1967) 493
25. P. Neta, R.W. Fessenden, R.H. Schuler, *J. Phys. Chem.* **75** (1971) 1654.
26. A.J. Colussi, L.K. Weavers, M. Hoffmann, *J. Phys. Chem. A* **102** (1992) 6927.
27. K.S. Suslick, G. J. Price, *Annu. Rev. Mater. Sci.* **29** (1999) 295.



Sonolytic Oxidation of Tc(IV)O₂nH₂O Nanoparticles to Tc(VII)O₄ in Aqueous Solution

ORIGINALITY REPORT

%33
SIMILARITY INDEX

%14
INTERNET SOURCES

%31
PUBLICATIONS

%4
STUDENT PAPERS

PRIMARY SOURCES

1 Gertraud Mark, Armin Tauber, Rüdiger Laupert, Heinz-Peter Schuchmann, Dorothea Schulz, Andreas Mues, Clemens von Sonntag. "OH-radical formation by ultrasound in aqueous solution – Part II: Terephthalate and Fricke dosimetry and the influence of various conditions on the sonolytic yield", *Ultrasonics Sonochemistry*, 1998
Publication **%4**

2 www.annualreviews.org
Internet Source **%4**

3 I. Hernandez-Fuentes, A. Horta, L. Gargallo, C. Abradelo, M. Yazdani-Pedram, D. Radic. "Partial specific volumes of methylsuccinates and poly(itaconate)s", *The Journal of Physical Chemistry*, 1988
Publication **%4**

4 Kenji Okitsu, Hiroshi Nakamura, Norimichi Takenaka, Hiroshi Bandow, Yasuaki Maeda, Yoshio Nagata. "Sonochemical reactions **%2**

occurring in organic solvents: reaction kinetics and reaction site of radical trapping with 1,1-diphenyl-2-picrylhydrazyl", Research on Chemical Intermediates, 2004

Publication

5

Sayan, E.. "Optimization and modeling of decolorization and COD reduction of reactive dye solutions by ultrasound-assisted adsorption", Chemical Engineering Journal, 20060615

Publication

%2

6

Soloviev, M.. "Coating a stainless steel plate with silver nanoparticles by the sonochemical method", Ultrasonics - Sonochemistry, 201101

Publication

%2

7

Dai, Y.. "Mechanism of the enhanced degradation of pentachlorophenol by ultrasound in the presence of elemental iron", Journal of Hazardous Materials, 20061011

Publication

%1

8

Yoshio Nagata, Kyozo Hirai, Hiroshi Bandow, Yasuaki Maeda. "Decomposition of Hydroxybenzoic and Humic Acids in Water by Ultrasonic Irradiation", Environmental Science & Technology, 1996

Publication

%1

9

Yoshiteru Mizukoshi, Ryuichiro Oshima,

Yasuaki Maeda, Yoshio Nagata. "Preparation of Platinum Nanoparticles by Sonochemical Reduction of the Pt(II) Ion", Langmuir, 1999

Publication

% 1

10

Ph. Moisy, S. I. Nikitenko, L. Venault, C. Madie. "Sonochemical Dissolution of Metallic Plutonium in a Mixture of Nitric and Formic Acid", Radiochimica Acta, 1996

Publication

% 1

11

www.journal.csj.jp

Internet Source

% 1

12

Submitted to Higher Education Commission Pakistan

Student Paper

% 1

13

www.journalrepository.org

Internet Source

% 1

14

www.freepatentsonline.com

Internet Source

% 1

15

Ben Nanzai. "Effects of initial concentration of LASs on the rates of sonochemical degradation and cavitation efficiency", Research on Chemical Intermediates, 10/13/2009

Publication

% 1

16

Gareth J. Price, Muthupandian Ashokkumar, Franz Grieser. "Sonoluminescence Emission from Aqueous Solutions of Organic Monomers",

% 1

17

Kenji Okitsu, Takeru Suzuki, Norimichi Takenaka, Hiroshi Bandow, Rokuro Nishimura, Yasuaki Maeda. "Acoustic Multibubble Cavitation in Water: A New Aspect of the Effect of a Rare Gas Atmosphere on Bubble Temperature and Its Relevance to Sonochemistry", The Journal of Physical Chemistry B, 2006

Publication

% 1

18

M. Chotkowski, M. Grdeń, B. Wrzosek. "Intermediate oxidation states of technetium in alkaline solutions", Journal of Electroanalytical Chemistry, 2018

Publication

<% 1

19

Ince, N.H.. "Sonochemical destruction of nonylphenol: Effects of pH and hydroxyl radical scavengers", Journal of Hazardous Materials, 20091230

Publication

<% 1

20

www.faqs.org

Internet Source

<% 1

21

Nikolopoulos, A.N.. "Ultrasound assisted catalytic wet peroxide oxidation of phenol: kinetics and intraparticle diffusion effects", Ultrasonics - Sonochemistry, 200601

<% 1

22

www.fulviofrisone.com

Internet Source

<% 1

23

Katy Ben Said, Yann Seimbille, Massoud Fattahi, Chantal Houee-Lévin, Jean Charles Abbé. "Gamma radiation effects on potassium pertechnetate in carbonate media", Applied Radiation and Isotopes, 2001

Publication

<% 1

24

myweb.dal.ca

Internet Source

<% 1

25

Kenji Okitsu, Itsuya Kurisaka, Ben Nanzai, Norimichi Takenaka, Hiroshi Bandow. "Sonochemistry of aqueous NaAuCl₄ solutions with C₃–C₆ alcohols under a noble gas atmosphere", Ultrasonics Sonochemistry, 2018

Publication

<% 1

26

Ben Nanzai, Kenji Okitsu, Norimichi Takenaka, Hiroshi Bandow, Yasuaki Maeda. "Sonochemical degradation of various monocyclic aromatic compounds: Relation between hydrophobicities of organic compounds and the decomposition rates", Ultrasonics Sonochemistry, 2008

Publication

<% 1

27

R. Vijaya Kumar. "Fabrication of magnetite

<% 1

nanorods by ultrasound irradiation", Journal of Applied Physics, 2001

Publication

28

B NANZAI, K OKITSU, N TAKENAKA, H BANDOW, N TAJIMA, Y MAEDA. "Effect of reaction vessel diameter on sonochemical efficiency and cavitation dynamics", Ultrasonics Sonochemistry, 2009

Publication

29

Okitsu, K.. "Effect of carbon tetrachloride on sonochemical decomposition of methyl orange in water", Chemosphere, 200803

Publication

30

www.nrcresearchpress.com

Internet Source

31

Fredrickson, J.K.. "Oxidative dissolution potential of biogenic and abiogenic TcO_2 in subsurface sediments", Geochimica et Cosmochimica Acta, 20090415

Publication

32

Wang, X.. "Chemical effect of swirling jet-induced cavitation: Degradation of rhodamine B in aqueous solution", Ultrasonics - Sonochemistry, 200804

Publication

33

www.lmbe.seu.edu.cn

Internet Source

<% 1

<% 1

<% 1

<% 1

<% 1

<% 1

34

K Okitsu. "Formation of noble metal particles by ultrasonic irradiation", *Ultrasonics Sonochemistry*, 1996

Publication

<% 1

35

www.radiochem.org

Internet Source

<% 1

36

pubs.rsc.org

Internet Source

<% 1

37

Pinkerton, T.C.. "The electrochemical reduction of pertechnetate in aqueous hydroxyethylidene diphosphonate media", *Journal of Electroanalytical Chemistry*, 19831125

Publication

<% 1

38

Kubo, M.. "Kinetics of ultrasonic degradation of phenol in the presence of TiO₂ particles", *Ultrasonics - Sonochemistry*, 200503

Publication

<% 1

39

Chotkowski, M., and A. Czerwiński. "Electrochemical and spectroelectrochemical studies of pertechnetate electroreduction in acidic media", *Electrochimica Acta*, 2012.

Publication

<% 1

40

Qiu, G.. "Ultrasonically initiated emulsion polymerization of styrene in the presence of Fe²⁺", *Ultrasonics - Sonochemistry*, 200804

Publication

<% 1

41

Hiroshi Moriwaki, Youichi Takagi, Masanobu Tanaka, Kenshiro Tsuruho, Kenji Okitsu, Yasuaki Maeda. "Sonochemical Decomposition of Perfluorooctane Sulfonate and Perfluorooctanoic Acid", Environmental Science & Technology, 2005

Publication

<% 1

EXCLUDE QUOTES ON

EXCLUDE BIBLIOGRAPHY ON

EXCLUDE MATCHES < 5 WORDS