

Potential_of_Expansive_Soil,_Tj aronge_et_al-2012-ISLT-Bali-.pdf

by

FILE	POTENTIAL_OF_EXPANSIVE_SOIL,_TJARONGE_ET_AL-2012-ISLT-BALI-.PDF (289.75K)		
TIME SUBMITTED	22-JUN-2020 02:40PM (UTC+0700)	WORD COUNT	2384
SUBMISSION ID	1347923848	CHARACTER COUNT	10857

EFFECT OF CONCRETE WASTE AS STABILIZATION MATERIAL ON CBR VALUE AND SWELLING POTENTIAL OF EXPANSIVE SOIL

M. W. Tjaronge¹, I. Maricar², A.B. Muhiddin³ and M. Sutiono⁴

12

ABSTRACT: The objective of this research is to improve expansive soil as a construction material using concrete waste, which is recognized as an environmental pollutant. The relationships between the amount of concrete waste with the compaction blows, curing days, CBR values, and swelling³ potential values was studied in this research. The test results show that replacing expansive soil by concrete waste formed a strong bond between the soil particles and the cementitious compound, resulting in the improvement of CBR values and the inhibition of soil swelling and shrinkage.

Keywords: Concrete waste, CBR value, swelling potential, compaction blows, curing days

INTRODUCTION

There are many locations in Indonesia contain expansive soil that shows shrinking and swelling movements which cause damage to road bases, embankments, and foundations of dwelling houses.

Demolition of old bridges, old buildings and buildings damaged by earthquakes or fires produce concrete waste. In addition, sometimes some productions do not meet the¹¹ standards and become waste material in the numbers of ready mix concrete plants, and precast concrete plants. The concrete waste is recognized as an environmental pollutant, its increase could harm the ecosystem surrounding dumping area. In order to reduce¹⁰ the increase of concrete waste, this material could be used as the construction material. The utilization of waste concrete as material construction has benefits in environmental protection and sustainable development. The waste concrete still⁷ contains calcium hydroxide, $\text{Ca}(\text{OH})_2$; therefore, it can be used as stabilization material of expansive soil.

This research tried to use the waste concrete to stabilize the expansive soil by replacing the expansive soil with concrete waste up to 40% by weight. The relationships between the amount of waste concrete with the compaction blows, curing days, CBR values and swelling potential values were studied in this research.

MATERIALS AND EXPERIMENTAL METHODS

Testing Method for Soil Properties

Some series of testing were conducted to find out the physical properties and chemical compound⁹ soil. Table 1 shows some testing to determine the physical properties of soil used in this research.

Table 1. Testing Method for Physical Properties

Physical Properties	Test Method
1. Specific Gravity	
2. Atterberg Limits	⁴
a. Liquid Limit (LL)	SNI 1966:2008
b. Plastic limit (PL)	SNI 1966:2008
c. Plasticity index	SNI 1966:2008
d. Shrinkage Limit (SL)	SNI 3422-2008
3. Grain size distribution	SNI 3423:2008
4. Level of activity (A_c)	
5. Soil Classification	a. USCS b. ASSHTO
6. Standard Proctor (compaction)	SNI 03-1742:1989
W_{opt} and γ_d	

1

¹ Professor, Department of Civil Engineering, Hasanuddin University, Makassar, 90245 INDONESIA

² Associate Professor, Department of Civil Engineering, Hasanuddin University, Makassar, 90245 INDONESIA

³ Associate Professor, Department of Civil Engineering, Hasanuddin University, Makassar, 90245 INDONESIA

⁴ Student, Department of Civil Engineering, Hasanuddin University, Makassar, 90245 INDONESIA

Waste Concrete Grain

Waste concrete was crushed to divide it into the coarse aggregates and grains of mortar or cement paste. Heretofore, the grains of mortar or paste cement are called waste concrete grain in this research. This grain was further pulverized so that it can pass through number 4 sieve. Chemical test was conducted to find out the chemical compound of the waste concrete grain.

Composition of Waste Concrete Grain and Soil

The composition of soil and waste concrete grain is shown in Table 2. Waste concrete grain was added up to 40% in this research. The addition of waste concrete grain was followed by the reduction of soil in order to keep the constant weight of mix.

Table 2 Composition of Waste Concrete Grain and Soil

Composition of Waste concrete grain and Soil	
Soil	Waste Concrete
90%	10 %
80%	20%
70%	30%
60%	40 %

Compaction, CBR Test, and Swelling Potential Test

Compaction of the expansive soil specimens was carried out in accordance to Indonesian standard, SNI 03-1742:1989. The number of blows were made varies, 30, 40 and 60 blows. After compacted, the specimens were prepared for CBR test and swelling potential test. The curing days were 7, 14 and 28 days. Testing for CBR soaked soil and CBR unsoaked soil were conducted in accordance to SNI 03-1744:1989. Testing for potential swelling was conducted by using the test piece of CBR soaked soil as shown in Figure 1. The swelling height was measured and compared to the initial height of test piece.



Fig. 1 Swelling Potential Test

RESULTS AND DISCUSSION

Expansive Soil

The physical properties and some chemical compounds of soil used in this research were shown in Table 3 and Table 4, respectively. Its properties show that the soil can be categorized as expansive soil.

Table 3 Physical properties of expansive soil

Physical Properties	Value
1. Specific Gravity	2.67
2. Atterberg Limits	
a. Liquid Limit (LL)	61.54%
b. Plastic limit (PL)	24.36%
c. Plasticity index	37.19%
d. Shrinkage Limit (SL)	10.95%
3. Grain size distribution (Sieve analysis reported that 50% of soil passed the sieve number of 200)	
a. Clay	23%
b. Silt	77%
4. Level of activity (A_c)	
	2.86 (active)
5. Soil Classification	
a. USCS	CH
b. ASSHTO	A-7
6. Standard Proctor (compaction)	
a. W_{opt}	24.02%
a. γ_d	1.57 gr/cm ³

Table 4 Chemical compounds of soil

Chemical Compound	Value (%)
SiO ₂	62.25
Al ₂ O ₃	15.12
Fe ₂ O ₃	4.5

Waste Concrete Grain

The results of chemical test showed the waste concrete grain containing 15.56% of Ca(OH)₂ by weight.

CBR Value

Table 5 and Table 6 show the results of CBR unsoaked test and CBR soaked test, respectively. The results are based from three measurements for each data point. In comparison by curing days, at the same number of the compaction blows, the CBR value became higher with the increase in curing days. Without the addition of concrete waste grain, the expansive soil can be compacted and achieve CBR value of 7.31% and 5.7% with 28 days curing time for unsoaked soil, and soaked soil, respectively.

In general, all of the CBR values increased with the increased of percentage of concrete waste grain that added to replace some part of the expansive soil.

The replacement of the expansive soil by the concrete waste grain up to 40% by weight, with the increase in the number of compaction blows and curing days made the expansive soil more stable and achieved CBR value of 46.04% and 42.02% with 28 days curing time for unsoaked soil, soaked soil, respectively.

The significantly increase in CBR value that observed after the addition of the concrete waste grain can be explained due to the development of chemical process between Ca(OH)₂ in concrete waste grain and minerals compound of soil (SiO₂, Al₂O₃, Fe₂O₃).

The chemical process increased the volume of the cementitious compound (CaO.2SiO₂.3H₂O) that made the soil stronger, more stable and led to improvement in CBR value.

The relationships between the amount of waste concrete with the compaction blows, curing days, CBR value of unsoaked soil and CBR value of soaked soil are described in Equation 1 and 2, respectively. These equations show the improvement of all the CBR values were influenced by the addition of the concrete waste, the numbers of compaction blows and the curing days.

$$\hat{y} = -6.09 + 0.81 x_1 + 0.15 x_2 + 0.40 x_3 \quad (1)$$

where:

\hat{y} = CBR value of unsoaked soil (%)

x_1 = the content of wasted concrete grain (%)

$\{x_1|0 \leq x_1 \leq 40\}$

x_2 = compaction blows $\{x_2|10 \leq x_2 \leq 65\}$

x_3 = curing days $\{x_3|7 \leq x_3 \leq 28\}$

$$\hat{y} = -6.67 + 0.70 x_1 + 0.12 x_2 + 0.36 x_3 \quad (2)$$

where:

\hat{y} = CBR value of unsoaked soil (%)

x_1 = the content of wasted concrete grain (%)

$\{x_1|0 \leq x_1 \leq 40\}$

x_2 = compaction blows $\{x_2|10 \leq x_2 \leq 65\}$

x_3 = curing days $\{x_3|7 \leq x_3 \leq 28\}$

Table 5 Test Results of CBR unsoaked soil

Expansive soil	Waste Concrete		CBR unsoaked (%)									
			7 days			14 days			28 Days			
			10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows	
%	kg	%	kg									
100	5	0	0	1.6	3.57	4.33	3.06	4.11	4.50	5.06	5.38	7.31
90	4.95	10	0.55	6.63	15.43	16.29	9.39	17.30	17.54	16.08	20.70	24.54
80	4.4	20	1.1	9.36	18.38	22.98	17.31	26.80	30.30	19.24	27.43	33.78
70	3.85	30	1.65	22.06	24.11	28.93	22.94	33.52	34.38	27.21	37.28	40.41
60	3.3	40	2.2	26.15	28.82	32.64	35.57	40.64	45.81	40.48	43.66	46.04

Table 6 Test Results of CBR soaked soil

Expansive soil	Waste Concrete		CBR soaked (%)									
			7 days			14 days			28 Days			
			10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows	
%	kg	%	kg									
100	5	0	0	1.38	2.33	3.35	2.42	3.17	3.36	3.60	4.78	5.70
90	4.95	10	0.55	5.53	8.29	11.02	7.21	9.32	11.06	12.90	16.87	19.52
80	4.4	20	1.1	9.35	12.82	15.51	10.52	13.68	19.30	17.32	24.91	31.50
70	3.85	30	1.65	19.70	21.65	25.97	20.95	23.90	28.21	23.19	27.15	32.50
60	3.3	40	2.2	23.77	25.52	30.15	28.26	32.82	35.75	28.70	38.02	42.02

Table 7 Result of Swelling Potential Test

Expansive soil		Waste Concrete		Swelling Potential (%)								
%	kg	%	kg	7 days			14 days			28 days		
				10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows	10 Blows	35 Blows	65 Blows
100	5	0	0	5.95	5.12	4.56	5.26	4.90	4.33	4.38	4.13	3.23
90	4,95	10	0,55	4.36	4.16	4.04	3.08	3.04	2.94	1.64	1.54	1.44
80	4,4	20	1,1	2.31	2.19	2.04	0.71	0.64	0.60	0.44	0.34	0.34
70	3,85	30	1,65	0.618	0.59	0.54	0.42	0.34	0.26	0.21	0.19	0.18
60	3,3	40	2,2	0.250	0.18	0.14	0.11	0.06	0.05	0.04	0.01	0.04

Potential Swelling

Table 7 shows the results of Potential Swelling test. The results are based from three measurements for each data point. At the soil without addition of concrete waste grain, after compacted the soil with 65 blows and cured up to 28 days, the soil had the potential value of 3.23%. This results revealed the soil can generate swelling and shrinkage movements, therefore it can be categorized as expansive soil.

The potential swelling value decreased with the increase in compaction blow and the period of curing for all percentages of concrete waste grain added as described in Table 7. The decline trend of swelling potential result was attributed to the development of the cementitious compound that also decreased the porosity of expansive soil that led to the decrease of the capacity of the water to enter into the pore spaces of the soil, and resulting in the reduction of the swelling potential value.

At the expansive soil that replaced with 20% of concrete waste grain, the compaction with 10 blows, and curing days of 14 days made the potential swelling value became less than 1%. At the expansive soil that replaced with 30% of concrete waste grain, all of the swelling potential value became less than 1%. At the expansive soil that replaced with 40% of concrete waste grain, the swelling potential value became less than 0.1% by compaction with 35 blows, and curing days of 14 days. For 28 days of curing, the compaction with 10 blows can reduce the potential swelling value to less than 0.1%.

Equation 3 shows the improvements of all the swelling potential value that were influenced by the addition of the concrete waste, the numbers of compaction blows and the curing days.

$$\hat{y} = 5.32 - 0.12x_1 - 0.01x_2 - 0.06x_3 \quad (3)$$

where :

\hat{y} = the swelling potential value (%)

x_1 = the content of waste concrete grain (%)
 $\{x_1 | 0 \leq x_1 \leq 40\}$

x_2 = compaction blows $\{x_2 | 10 \leq x_2 \leq 65\}$

x_3 = curing days $\{x_3 | 7 \leq x_3 \leq 28\}$

CONCLUSIONS

1. Replacing of the expansive soil by the concrete waste formed the strong bond between the soil particle and the cementitious compound, resulting in the improvement of CBR value.
2. The strong bond between the soil particle and the cementitious compound improved the compactness of soil, which then led to soil impermeability and inhibit swelling and shrinkage.

REFERENCES

Neville A.M., 1995, Properties of Concrete, Prentice Hall.

Robert M. Brooks, (2009), Soil Stabilization with Fly Ash and Rice Husk Ash, International Journal of Research and Reviews in Applied Sciences, Volume 1, Issue 3, pp.209-217

SNI 1966:2008, Standard Method of Test for Determining the Plastic Limit and Plasticity Index of Soil.

SNI 3422:2008, Testing Method for Determining the Shrinkage Limit of Soil.

SNI 3423:2008, Standard Method of Test for Particle Size Analysis of Soils.

SNI 1966:2008, Standard Method of Test for Determining the Plastic Limit and Plasticity Index of Soil.

SNI 03-1742:1989, Moisture-Density Relations of Soils Using a 2.5 kg of Rammer and a 305 mm Drop.

SNI 03-1744:1989 Standard Method of Test for The California Bearing Ratio (in laboratory)

Yashuhiro Dosho, (2007), Development of a Sustainable Concrete Waste Recycling System, Journal of Advanced Concrete Technology Vol.5, No.1, pp.27-42

ORIGINALITY REPORT

%**9**

SIMILARITY INDEX

%**6**

INTERNET SOURCES

%**6**

PUBLICATIONS

%**6**

STUDENT PAPERS

PRIMARY SOURCES

- 1** Tjaronge, M. Wihardi, Rita Irmawaty, Sakti Adji Adisasmitha, Arwin Amiruddin, and Hartini. "Compressive Strength and Hydration Process of Self Compacting Concrete (SCC) Mixed with Sea Water, Marine Sand and Portland Composite Cement", Advanced Materials Research, 2014. %**2**
Publication
- 2** cot.unhas.ac.id %**2**
Internet Source
- 3** Submitted to De La Salle University - Manila %**1**
Student Paper
- 4** H Asnur, R Yuliet, A Hakam, H G Putra, Sunaryo. "Effects of water content to slope stability in Pangkalan Lima Puluh Kota", IOP Conference Series: Earth and Environmental Science, 2019 %**1**
Publication
- 5** link.springer.com

6

Submitted to Cyprus International University

Student Paper

<% 1

7

I Rauf, L Samang, T Harianto, A Arsyad.

"Compressive strength of lightweight geocomposit soil-eps stabilized with palm oil-tea fly ash", IOP Conference Series: Earth and Environmental Science, 2020

Publication

<% 1

8

gndec.ac.in

Internet Source

<% 1

9

Submitted to Institute of Graduate Studies, UiTM

Student Paper

<% 1

10

Erdawaty, L Samang, A B Muhiddin, A Arsyad.

"Characteristics study of buton granular asphalt as filling material of column", IOP Conference Series: Earth and Environmental Science, 2020

Publication

<% 1

11

issuu.com

Internet Source

<% 1

12

www.ijsrp.org

Internet Source

<% 1

13

Xianmin Li, , Mengshu Wang, and Yanhui Liang.

"Study on treatment theory and technique for

<% 1

expansive soil geological disasters", 2011
International Conference on Remote Sensing
Environment and Transportation Engineering,
2011.

Publication

EXCLUDE QUOTES ON

EXCLUDE
BIBLIOGRAPHY ON

EXCLUDE MATCHES < 5
WORDS